

Co-polymer 12 Plait

Co-polymer Olefin 12 Plait provides high strength, light weight and excellent abrasion resistance in a single braid construction.

Co-polymer Olefin 12 Plait is easily spliced using a standard tuck splice and is 40% stronger than three strand or 8 plait polypropylene. Its torque free braided construction provides easy handling and prevents kinks and hockles.

Features & Benefits

- Floats
- High strength
- Excellent abrasion resistance
- Torque free
- Easy splicing
- Excellent UV resistance

Applications

- Floating mooring lines for barges/vessels
- Floating winch lines
- Subsea buoy moorings
- Lashings

Nominal Diameter		Size (circ in.)	Approximate Weight		Minimum Tensile Strength Spliced Rope		Minimum Tensile Strength ISO Unspliced Rope	
inch	mm		lbs/100ft	kg/100m	lbs	MT (tonnes)	lbs	MT (tonnes)
5/8	16	2	8.6	12.8	8,300	3.8	9,200	4.2
3/4	18	2-1/4	10.8	16.1	12,300	5.6	13,600	6.2
7/8	22	2-3/4	14	20.8	14,200	6.4	15,700	7.2
1	24	3	20.3	30.2	20,100	9.1	22,300	10.1
1-1/8	28	3-1/2	24.5	36.5	24,000	10.9	26,600	12.1
1-1/4	30	3-3/4	27	40.2	26,000	11.8	28,800	13.1
1-5/16	32	4	31.9	47.5	29,900	13.6	33,200	15.1
1-1/2	36	4-1/2	39.2	58.3	39,400	17.9	43,700	19.9
1-5/8	40	5	50.4	75	49,000	22.2	54,400	24.7
1-3/4	44	5-1/2	58.8	87.5	54,600	24.8	60,600	27.5
2	48	6	71.4	106.3	69,700	31.6	77,400	35.1
2-1/8	52	6-1/2	84	125	80,900	36.7	89,800	40.8
2-1/4	56	7	96.6	143.8	92,200	41.8	102,400	46.5
2-1/2	60	7-1/2	109	162.2	103,300	46.8	114,700	52.1
2-5/8	64	8	126	187.5	119,900	54.4	133,200	60.4
2-3/4	68	8-1/2	132	196.4	136,500	61.9	151,600	68.8
3	72	9	160	238.1	153,000	69.4	170,000	77.1
3-1/4	80	10	193	287.2	194,900	88.4	216,500	98.2
3-5/8	88	11	238	354.2	220,000	99.8	244,400	110.9
4	96	12	280	416.7	250,000	113.4	277,700	126.0


Tensile Strengths are determined in accordance with Cordage Institute 1500, Test Methods for Fiber Rope. Weights are calculated at linear density under standard preload (200d²) plus 4%. See reverse side for application and safety information.

Technical Information

Specific gravity	0.94*
Melting point	279°F (137°C)
Critical temp.	140°F (60°C)
Coefficient of friction	0.16–0.018*
Elongation at break	20–25%
Fiber water absorption	0–1%
UV resistance	excellent
Wet abrasion	very good
Dry abrasion	excellent

* value based on data supplied by the fiber manufacturer for new, dry fiber

Co-polymer 12-Plait Elongation (%)



Co-polymer 12 Plait

Rope Specifications

Minimum Tensile Strength Minimum tensile strengths shown are for new (unused) rope and will decrease after use. All tests are performed in accordance with Cordage Institute Standard CI 1500-2. The rope strength will be reduced after use due to heat, abrasion, ultraviolet or chemical exposure. The tensile strengths may be further reduced by up to 50% as a result of knots or kinks. Minimum tensile strengths are defined as two standard deviations (typical about 10%) below the average.

Maximum Working Loads Maximum working loads are determined by dividing the tensile strength by the safety factor. The safety factor is a function of the physical properties of the rope, the age and history of the rope, the type of service it will be subjected to and the risks involved if failure occurs. For a rope manufacturer to give blanket working load recommendations would be like a car manufacturer giving the “safe driving speed” of their cars. Obviously the conditions of use far outweigh the design characteristics of the rope. Typically safety factors vary from 3:1 (for new rope used in applications with uniform loading and where failure would cause little or no risk to equipment or personnel) to 20:1 (for conditions involving moderate shock loading, possibility of snags or kinks or where failure could cause severe risk to equipment or personnel).

Rope Weights Rope weights shown are average and may vary plus or minus 5%.

Working Elongation Working elongation is shown from a preload tension of 200 times the diameter squared per the Cordage Institute Standard.

Special Requirements

Factory Splicing Various types are available for all of our ropes. Splices can be provided with various types of chafe protection or coatings.

Custom Lengths Special constructions are available on request.

Rope Terminations Cortland can provide custom terminations such as thimbles, links, rings and custom hardware. Terminations are available in plastic, bronze, stainless steel and galvanized steel. Please call, or email your requirements to cortland@cortlandcompany.com for a quotation.

Special Coatings Coatings such as polyurethane, polyethylene and vinyl esters may be applied to any of the synthetic ropes to improve snag resistance, sunlight resistance or for color coding. Cortland can provide ropes with a variety of finishes to meet your needs.

Commercial and Military Specifications Certificates of compliance are supplied at no charge if requested when placing the order. Certified test reports can be provided at an additional charge when requested at the time of the order.